




I cores

IP3. 2X2X2.5




CORE SETS

CORE DIMENSIONS (mm)

Dimensions (mm)								Weight (g)
A	B	C	D	E	F	H	G	
3.2±0.08	2.5±0.08	2.5±0.08	1.1±0.08	0.45±0.08	0.95±0.08	2.0±0.08	1.2±0.08	0.02

Characteristic

Grade	$L (\mu H)$	$L_{0.2A} (\mu H)$
		$f=100kHz$ $U=1.0V$ $N=20T_s, \Phi 0.2 \text{ mm}$
DN40B	$6.5 \pm 20\%$	$\geq 90\% \times L_{0A}$



CORE SETS

CORE DIMENSIONS (mm)

Dimensions (mm)								Weight (g)
A	B	C	D	E	F	H	G	
4.5±0.1	3.2±0.1	3.7±0.1	1.65±0.1	0.6±0.1	1.35±0.1	2.65±0.1	1.65±0.08	0.05


Characteristic

Grade	L (μH)	L _{0.4A} (μH)
		f=100kHz U=1.0V N=20Ts, Φ0.2 mm
DN35H	10.0±20%	≥90% X L _{0A}



I cores

IP6X3X4. 2



CORE SETS

CORE DIMENSIONS (mm)

Dimensions (mm)							Weight (g)
A1	A2	B	ΦC	D	E	F	
6.0±0.1	6.0±0.1	4.2±0.1	3.0±0.1	0.8±0.1	2.3±0.1	1.1±0.1	0.45


Characteristic

Grade	L (μH)	L _{2.0A} (μH)
		f=100kHz U=1.0V N=20Ts, Φ0.2 mm
DN40B	12.4±20%	≥90% X L _{0A}

I cores



IPY8X3. 3X3. 65



CORE SETS

CORE DIMENSIONS (mm)

Dimensions (mm)										Weight (g)
A1	A2	A3	A4	B	ΦC	D	E	F	G	
8±0.15	8±0.15	7.5±0.1	8±0.15	3.65±0.1	3.3±0.1	0.7±0.1	2.0±0.1	0.95±0.1	4.0±0.3	0.63

Characteristic

Grade	L (μH)	L _{2.2A} (μH)
	f=100kHz U=1.0V N=20Ts, Φ0.35 mm	f=100kHz U=1.0V N=20Ts, Φ0.35 mm
DN40B	19.0 ± 20%	≥85% X L _{0A}