



材料特性表

General Material performance

DMEGC MIX NO.	Reference Permeability (μ_e)	Temperature Stability(ppm/)	Toroidal Color Code
-1	20	280	Light green
-2	10	95	Red
-3	35	370	Hoar whtie
-6	8.5	35	Dark pea green
-7	9	30	Iron oxide red
-8	35	255	Bright green
-10	6	150	Grass green
-15	25	190	White
-18	55	385	Green
-26	75	825	Yellow
-28	22	415	Sky blue
-33	33	635	Gray
-34	33	565	Dark blue
-35	33	665	Light gray
-38	85	955	Black
-40	60	950	Green
-52	75	650	Blue
-118	35	560	Black

尺寸公差

Dimensional Tolerance(Includes coating)

Toroids	OD(mm)		ID(mm)		HT(mm)	
DT14~DT72	± 0.50		± 0.50		± 0.50	
DT80~DT141	± 0.50		± 0.50		± 0.50	
DT150~DT225	± 0.64		± 0.64		± 0.76	
DT249~DT400	± 0.76		± 0.76		± 0.76	
DT520~DT650	± 1.27		± 1.27		± 1.27	
E Core	A(mm)	B(mm)	C(mm)	D(mm)	F(mm)	G(mm)
DE49~DE118	± 0.25	± 0.25	± 0.13	± 0.18	± 0.13	± 0.18
DE125~DE162	± 0.38	± 0.38	± 0.18	± 0.25	± 0.18	± 0.25
DE168~DE225	± 0.38	± 0.38	± 0.25	± 0.50	± 0.38	± 0.50
DE305~DE450	± 0.76	± 0.76	± 0.38	± 0.50	± 0.38	± 0.50

电感公差

Inductance tolerance

材质	-2、-6、-7、-10、-17	-1、-3、-8、-15、-18、-26、-28、-33、-34、-35、-38、-40、-45、-52
公差	± 5%	± 10%











